

EFFECT TECHNICAL SHEET

PEARL STUCCO MATT

Classic Effect



DECORATIVE EFFECT DESCRIPTION:	PEARL STUCCO MATT Classic Effect is a decorative effect with a delicate, velvety character.
USE:	Indoors
TINTING	Can be tinted with Cameleo pigments
SUBSTRATE PREPARATION:	In accordance with the PEARL STUCCO MATT Product Technical Data Sheet.
PRODUCT PREPARATION:	In accordance with the PEARL STUCCO MATT Product Technical Data Sheet.
STAGES OF APPLICATION:	
PRODUCTS USED FOR THE EFFECT:	The Cameleo decorative effect should be prepared and applied by a trained applicator.
1. Primer (optional):	CAMEPRIMER P100 Consumption up to: 0.115 l/m² Application tools: Paint roller, brush Application: Apply one coat of CAMEPRIMER P100 primer to the properly prepared substrate using a paint roller. Drying time: 2 h
2. Undercoat:	CAMEPRIMER P300 Consumption up to: 0.115 l/m² Application tools: Paint roller, brush Application: Apply one coat of CAMEPRIMER P300 undercoat in the appropriate colour to the properly prepared substrate using a paint roller. Drying time: 2 h
3. Textured paint:	PEARL STUCCO MATT (first coat) Consumption up to: 0.17 l/m²



Application tools: Flexible Venetian trowel

Apply a coat of PEARL STUCCO MATT textured paint to the properly prepared substrate using a flexible Venetian trowel. Apply it evenly to avoid thick areas. Work continuously until the entire surface is covered with PEARL STUCCO MATT textured paint. Leave to dry.

Drying time: 4 h

4. Textured paint: PEARL STUCCO MATT (second coat)

Consumption up to: 0.04 l/m²

Application tools: Flexible Venetian trowel, flexible oval trowel

Using the Venetian trowelling technique (small, short strokes), cover the entire first coat of textured paint to create a subtle pattern. Work continuously until the entire surface is covered with PEARL STUCCO MATT textured paint. Leave to dry.

Drying time: 4 h

EFFECT At 20°C and 50% air humidity:

DRYING TIME:

Touch dry: 2 h after application of the final coat

Fully cured: After 7 days

TOOL CLEANING: Warm soapy water

SURFACE CLEANING: The surface may be washed 14 days after completion of the full application process. Do not use detergents. Clean with soap and water.

APPLICATION CONDITIONS: Application temperature: +10°C - +30°C. Minimum substrate temperature: +10°C. Maximum substrate temperature: +30°C. Substrate moisture content must not exceed 4%. Maximum air humidity: 75%.

NOTES: The Effect Technical Sheet describes the decorative effect and its application stages. It does not guarantee correct execution of the effect. The final appearance of the surface to which the decorative technique is applied depends on the applicator's individual working method and experience. A trial application on a sample area is recommended before starting the decorative work.



EFFECT TECHNICAL SHEET

PEARL STUCCO

Classic Effect

EN VERSION 7.0, DATE: 12-01-2026

www.cameleo.pl

For areas exceeding 10 m², work in teams of 2 - 3 people. The effect can be applied by one person if the surface is divided into smaller sections. The recommended area for one person should not exceed 10 m². For surfaces higher than 3 m, the use of scaffolding is recommended.

WARRANTY:

Product warranty: Cameleo Leśniewicz Gradowska Spółka Jawna warrants that Cameleo products are of merchantable quality and comply with the standards declared by Cameleo. Cameleo products are covered by warranty provided that they are used in accordance with the instructions in the Product Technical Data Sheets and Effect Technical Sheets. Products are not covered by warranty if they are not used in accordance with the information in the Product Technical Data Sheets and Effect Technical Sheets. Liability under this warranty (if the product proves defective) is strictly limited to replacement of the product or a refund of its purchase price. This warranty is valid for one year from the date of purchase of the product.

Effect warranty: Cameleo Leśniewicz Gradowska Spółka Jawna warrants that Cameleo effects are of merchantable quality and comply with the standards declared by Cameleo in the Product Technical Data Sheets and Effect Technical Sheets. Cameleo effects are covered by warranty provided that they have been applied by certified individuals or companies trained in professional application at Cameleo's premises or at the premises of a certified representative of Cameleo products in Poland or elsewhere in the world. Liability under this warranty (if the effect proves defective and was applied by a certified Cameleo applicator) is strictly limited to replacement of the products used to create the effect or a refund of their purchase price. This warranty is valid for 2 years from the date of purchase of the products used to create the effect.

MANUFACTURER:

CAMELEO Leśniewicz Gradowska Spółka Jawna, ul. Sikorskiego 139, 63-100 Psarskie. Tel. 61-28-35-899



EFFECT TECHNICAL SHEET

PEARL STUCCO

Classic Effect

EN VERSION 7.0, DATE: 12-01-2026

www.cameleo.pl