

PRODUCT TECHNICAL DATA SHEET

STONE FINISH

Decorative plaster

DESCRIPTION:	Thin-layer decorative plaster that imitates the texture of a cement floor. Natural fillers and high-quality additives give this effect exceptional durability.
COLOUR:	White base
TINTING METHOD	Can be tinted with Cameleo pigments.
SUBSTRATE PREPARATION:	Before applying the Cameleo decorative effect, prepare the substrate surface properly. - Concrete substrates Allow concrete substrates to cure for at least 30 days. The moisture content must not exceed 4%. The concrete substrate must be at least class C20/25 (B25). Remove all contamination and dirt mechanically. Apply a coat of CAMEPRIMER P3000 to the substrate prepared in this way.
PRODUCT PREPARATION:	Mechanically mix 12 kg of plaster with 240 ml of HARDENER H02 additive. Once mixed, use the entire mixture within 5 h. The plaster may be diluted with water up to 5% of its weight. Mixing time: approx. 1 min. When working on areas larger than the coverage of a single pack, mix the contents of the individual packs together in one container.
APPLICATION:	Flexible Venetian trowel
TECHNICAL INFORMATION:	Thinner - Water Specific gravity - 1.88 g/ml (with 2% HARDENER H02 additive) Consumption up to - 0.5 kg/m² (first coat), 0.3 kg/m² (second coat) Practical coverage - Coverage depends on many factors, such as substrate porosity and roughness, and material losses during application. pH - Approx. 8.8 (with 2% HARDENER H02 additive)
RECOMMENDED PRIMERS	CAMEPRIMER P100, CAMEPRIMER P3000
TOOL CLEANING:	Warm soapy water.



PRODUCT TECHNICAL DATA SHEET

STONE FINISH

Decorative plaster

EN VERSION 7.0, DATE: 12-01-2026

www.cameleo.pl

SURFACE CLEANING AND CARE	The surface may be washed 21 days after completion of the full application. Do not use detergents. Clean with soap and water.
PRODUCT DRYING TIME:	At 20°C and 50% air humidity: Touch dry - 6 hours after application. Cured - 14 days after application
APPLICATION CONDITIONS:	Application temperature: +10°C – +30°C. Minimum substrate temperature: +10°C. Maximum substrate temperature: +30°C. Substrate moisture content must not exceed 4%. Maximum air humidity: 75%
STORAGE AND TRANSPORT:	Store in tightly closed packaging at +5°C – +25°C. The product is sensitive to frost. Protect from sunlight. Shelf life: 12 months from the date of manufacture in the original sealed packaging (date of manufacture on the packaging).
PACK SIZES:	12 kg + H02 240 ml
SAFETY INFORMATION:	All product safety instructions are available in the Safety Data Sheet for the chemical substance (mixture).
VOC	VOC: 36 g/l VOC category: A/I VOC limit: 200 g/l
NOTES:	Mix the product thoroughly by mechanical means before use. When working on areas larger than the coverage of a single pack, mix the contents of the individual packs together in one larger container. The colours shown in the catalogue may differ from the actual colours on the wall. Colours depend on the application method, texture, gloss, lighting, sunlight, and the types and intensity of other surrounding colours. Storage, transport and application conditions, as well as the final effect, are beyond our control and therefore cannot constitute a guarantee in the legal sense. Statutory regulations and any third-party rights must be observed in all cases.
WARRANTY:	Cameleo Leśniewicz Grądkowska Spółka Jawna warrants that Cameleo products are of merchantable quality in accordance with the standards declared by Cameleo. Cameleo products are covered by warranty provided that they are used in accordance with the instructions in the Product Technical Data Sheets and Decorative Effect Technical Sheets. Products are not covered by warranty if they are not used in accordance with the information in the Product Technical Data Sheets and Decorative Effect Technical Sheets. Liability under this warranty (if the product proves defective) is strictly limited to



replacement of the product or a refund of its purchase price. This warranty is valid for one year from the date of purchase of the product.

MANUFACTURER: CAMELEO Leśniewicz Grądkowska Spółka Jawna, ul. Sikorskiego 139, 63-100 Psarskie. Tel. 61-28-35-899

